

SIL-ACT® Product Data

ATS-200

Alkyltrialkoxysilane



ADVANCED
CHEMICAL
TECHNOLOGIES, Inc.

"Protecting the World's Infrastructure"

HIGH PERFORMANCE

SIL-ACT® ATS-200 is a clear, penetrating silane treatment which causes concrete, masonry and many natural stones to become repellent to water, chloride, waterborne contaminants and weathering elements, preventing the premature deterioration of parking decks, bridge decks, pavements and other types of concrete and masonry structures. Performance testing makes SIL-ACT® ATS-200 an excellent choice for any project requiring the highest quality clear water repellent.

DURABLE

SIL-ACT® ATS-200 can be applied to the surface by low-pressure spray, brush, roller or squeegee. It can be stored on the jobsite at temperature extremes, eliminating storage problems associated with emulsified silane products that can deteriorate on the jobsite, prior to use, if not properly stored. SIL-ACT® ATS-200 chemically bonds with the substrate forming a penetrated layer below the surface that acts as a one-way filter. Water, chloride and other waterborne contaminants are repelled without restricting the substrates natural vapor permeability.

FLEXIBLE



SIL-ACT® ATS-200 is an effective treatment for brick, masonry, cementitious mortars, stucco, many natural stones and cast-in-place, precast, prestressed and architectural concretes.

Structures that can be treated include:

- Parking decks
- Bridges
- Commercial buildings
- Airport pavements
- Highways
- No masking of windows required
- Cooling towers
- Stadiums
- Other horizontal and vertical structures

STOPS
WATER
CHLORIDE
WATERBORNE
CONTAMINANTS

PERFORMANCE TESTED!



SIL-ACT®'s penetrated silane treatment layer stops water and salt intrusion into concrete, brick, masonry and many types of stone without affecting natural vapor permeability.

TECHNICAL DATA

PROPERTY	TEST	ATS-200
Active Ingredient		Alkyltrialkoxysilane
Specific Gravity @ 25°C	Method 24, ASTM D-5095	0.88
Density		7.34 lb/gal
Active Content		100% active Flash Point 141.8F/ 61°C (SCC)
VOC Content		< 390 g/L
Appearance		Colorless to pale yellow
Surface Appearance after Application		Unchanged
Drying time at 70°F		1 hour
Water Absorption	ASTM D-6489	0.1%
Depth of Penetration	OHD-L34	.16 to .2 Inch
Moisture Vapor Permeability	OHD-L35	99.6%
Scale Resistance	ASTM C-672	0 @ 100 Cycles
Moisture Absorption Resistance	ASTM C-642	.11 @ 48 Hours .34 @ 50 Days
Chloride Ion Reduction	AASHTO T 259	.22 @ 1/2 - Inch Depth .0 @ 1 - Inch Depth
Testing for Chloride Ion	AASHTO T 260	.05 @ 1/2 - Inch Depth .04 @ 1 - Inch Depth
Reduction in Absorbed Chloride	NCHRP 244 Series II	86%
	NCHRP 244 Series IV - Southern Climate	99%
Waterproofing After Abrasion	Alberta Trans. & Utilities (1c)	85.4%
Waterproofing After Abrasion	Alberta Trans. & Utilities (1b)	86.1%

INSTRUCTIONS

- Test a small area prior to general application to ensure compatibility, desired results and coverage rates.
- Treatment is most effective when the surface to be treated is clean and dry. Remove dirt, dust, oil, grease, curing compounds, coatings and other surface contaminants. Water blasting, sandblasting or shotblasting may be required.
- Please refer to Advanced Chemical Technology's CleanACT™ line of concrete and masonry detergents and cleaners.
- Do not proceed unless surface and air temperature is between 20°F and 110°F. Do not apply if frost, ice, or standing water are visible on the surface to be treated.
- Windows, metals, etc. are not affected by SIL-ACT® ATS-200. No masking of windows required. However avoid unnecessary overspray. If necessary, clean overspray areas with a clean dry cloth, soap and water or alcohol. Protect plants and vegetation from overspray. Prior to SIL-ACT® ATS-200 installation check for preexisting contamination.
- Spray, brush or roll SIL-ACT® ATS-200 treatment on surface to be treated at the recommended application rate. See equipment section of this catalog or contact your Advanced Chemical Technologies, Inc. representative for spray equipment options.
- Apply to saturation. When spraying at low pressure, if necessary follow with broom or squeegee for even distribution.
- Normal coverage rate is approximately 150 to 400 square feet per gallon.
- Clean equipment with SIL-ACT® Equipment Cleaner.
- Partially used containers should be properly sealed and protected from contamination by water or other foreign substances.
- Contact your Advanced Chemical Technologies, Inc. representative if you have questions regarding temperature and concrete moisture content concerns.

WARRANTY

Limited warranties are available for all SIL-ACT® products. Contact ACT or your local SIL-ACT® representative for details.

SIL-ACT® ATS-200 is covered by several patents including U.S. 4,931,319

NOTICE: This brochure was prepared as an introduction to a product manufactured by Advanced Chemical Technologies, Inc. The information provided herein is based upon typical installation conditions and is believed to be reliable. However, due to the wide variety of possible intervening factors, Advanced Chemical Technologies, Inc. does not warrant the expected results to be obtained. Details concerning product specifications and warranty may be obtained from Advanced Chemical Technologies, Inc. Specifications are subject to change. Sale of subject system is limited to Advanced Chemical Technologies, Inc. and authorized applicator's conditions of sale including those limiting warranties and remedies.

ADVANCED CHEMICAL TECHNOLOGIES, INC.

"Protecting the World's Infrastructure"

Technical Binder

